



System: TurboSeal

Application: Horizontal Decks, Balconies, Green Roofs

System Thickness: 106 mils (2.7 mm)

1st Layer

2nd Layer

3rd Layer

Product Name | Turbo Seal GT (90 mils | 2.3 mm)

GFG20X (16 mils | 0.8 mm)

e.drain 6000

DESCRIPTION

TurboSeal cold fluid-applied polymer rubber gel waterproofing assembly is comprised of a single-component, 75% solids, VOC-free monolithic fluid membrane that is protected by a high density polyethylene (HDPE) protection sheet to allow for immediate QA/QC. TurboSeal’s Polymer Rubber Gel Technology creates a non-curing, self-healing, and self-sealing waterproofing layer that is non-slumping, flexible, and does not off-gas or lose film thickness after application. TurboSeal assemblies dynamically respond to substrate movement, eliminate lateral water migration, and have excellent crack-bridging and crack-sealing capabilities.

TurboSeal - Horizontal Assembly is a redundant field-installed composite deck waterproofing system for traditional podium deck and green roof applications. Designed to be installed in most temperaure conditions and for projects where performance is paramount, TurboSeal - Horizontal Assembly combines the benefits of a self-healing and structurally responsive monolithic fluid applied waterproofing membrane with EPRO’s GFG Series HDPE vapor barrier protection course. Ideal for deck applications sloped to area drains with a minimum slope of 1/8” per lineal foot, TurboSeal - Horizontal Assemblies provide a reinforced fluid-applied deck solution that can be applied over green concrete, as a restoration membrane over previously applied waterproofing systems, and in below freezing weather conditions.

TurboSeal requires the use of a progressive cavity rotor stator pump for application.

TurboSeal - Horizontal Assembly can be used in conjunction with concrete topping slabs, pedestal and paver systems, and green roofs.

BENEFITS

- Self-heals damage to membrane.
- Self-seals cracks to prevent lateral water migration.
- No VOCs, no volume loss, and primer-free application.
- Seamless fluid application fully bonds to substrate.
- Composite assembly meets Class A vapor barrier standards.
- Fast installation in all temperatures (0 - 120°F | -18 - 49°C). Designed for new construction and green concrete applications.
- Designed to restoration applications over rough substrates and previously installed waterproofing.

LIMITATIONS

- Requires progressive cavity rotor stator pump for application
- TurboSeal must be installed with a protection course.

SYSTEM COMPONENTS

- Waterproofing: Turbo Seal GT
- Protection Course: GFG16, GFG20X
- Drainage Course: e.drain 6000
- Ancillary Products: e.poly, DuroTape, BentoTak, e.stop gu

SPECIFICATIONS, DRAWINGS, AND TECHNICAL ASSISTANCE

The most current specifications and drawings can be found on www.eproinc.com. For project specific details contact EPRO directly, or the local EPRO representative.

Site conditions, performance goals, and budget determine which system is more appropriate for a given project. For more information regarding product performance, testing, plan review, or general technical assistance, please contact EPRO.

WARRANTY

EPRO provides a wide range of warranty options for E.Series systems. For a project to be eligible for any warranty option beyond a 1-year material warranty, an EPRO Authorized Applicator must be used and the project must be registered and approved by EPRO prior to the commencement of any product application.

Warranty options available for this system include:

- Material warranty
- E.Series Labor and Material Warranty
- E.Assurance No-Dollar-Limit Warranty

For information relating to EPRO’s E.Assurance warranty program, contact EPRO. All E.Assurance no-dollar-limit labor and material warranties are approved on a project by project basis. E.Assurance warranties are available for deck applications when EPRO systems are used on the below-grade envelope.

Typical Physical Properties

| Physical Property | Test Method | Value |
|--|---------------------|--|
| Solids Content | ASTM D 1353 | 75-88% |
| VOC Content..... | ASTM D 1353 | 0% |
| Flash Point | ASTM D 56..... | > 200°F (>93°C) |
| Resistance to Decay | ASTM E 154-88 | 0% moisture permeation and weight change |
| Extensibility After Heat Aging | ASTM C 1522 | 1/4" (6.35 mm) No Cracking, Pass |
| Elongation | ASTM C 1135 | > 390% |
| Adhesion to Concrete | ASTM D 412-98 | Rating of 1 (Excellent) |
| Cold Temperature Crack Bridging..... | ASTM C 1305 | 5 of 5, Pass |
| Crack Bridging Flexibility..... | ASTM C 836-89 | No Cracks |
| Hardness, HDPE (GFG20X) | ASTM C 836-89 | 80 |
| Tensile Strength, HDPE (GFG20X) | ASTM D 412-98 | > 3891 psi (26.82 Mpa) |
| Puncture Resistance, HDPE (GFG20X) | ASTM E 154 | > 125 lbf (21,890 N/m) |
| Hydrostatic Pressure Resistance, HDPE (GFG20X) | ASTM C 1306 | 169 ± 3 psi |
| Permeance to Water Vapor Transmission, HDPE (GFG20X) | ASTM E 96-80 | < 0.005 perms |